

Preparation of steel substrates before application of paints and related products — Specification for non-metallic blast-cleaning abrasives —

Part 9: Staurolite

The European Standard EN ISO 11126-9:2004 has the status of a British Standard

ICS 25.220.10

National foreword

This British Standard is the official English language version of EN ISO 11126-9:2004. It is identical with ISO 11126-9:1999.

The UK participation in its preparation was entrusted to Technical Committee STI/21, Surface preparation of steel, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled “International Standards Correspondence Index”, or by using the “Search” facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, page ii, pages 1 to 4, an inside back cover and a back cover.

The BSI copyright notice displayed throughout this document indicates when the document was last issued.

This British Standard, having been prepared under the direction of the Sector Committee for Materials and Chemicals, was published under the authority of the Standards Committee and comes into effect on 15 August 1999

© BSI 25 April 2005

Amendments issued since publication

Amd. No.	Date	Comments
15512	25 April 2005	Implementation of the European Standard.

ICS 25.220.10

English version

Preparation of steel substrates before application of paints and related products - Specifications for non-metallic blast-cleaning abrasives - Part 9: Staurolite (ISO 11126-9:1999)

Préparation des subjectiles d'acier avant application de peintures et de produits assimilés - Spécifications pour abrasifs non métalliques destinés à la préparation par projection - Partie 9: Staurolite (ISO 11126-9:1999)

Vorbereitung von Stahloberflächen vor dem Auftragen von Beschichtungsstoffen - Anforderungen an nichtmetallische Strahlmittel - Teil 9: Staurolith (ISO 11126-9:1999)

This European Standard was approved by CEN on 21 December 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 11126-9:1999 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 11126-9:2004 by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 11126-9:1999 has been approved by CEN as EN ISO 11126-9:2004 without any modifications.

INTERNATIONAL
STANDARD

ISO
11126-9

First edition
1999-05-01

**Preparation of steel substrates before
application of paints and related products —
Specifications for non-metallic blast-
cleaning abrasives —**

**Part 9:
Staurolite**

*Préparation des subjectiles d'acier avant application de peintures et de
produits assimilés — Spécifications pour abrasifs non métalliques destinés
à la préparation par projection*

Partie 9: Staurolite



Reference number
ISO 11126-9:1999(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11126-9 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 12, *Preparation of steel substrates before application of paints and related products*.

ISO 11126 consists of the following parts, under the general title *Preparation of steel substrates before application of paints and related products — Specifications for non-metallic blast-cleaning abrasives*:

- *Part 1: General introduction and classification;*
- *Part 3: Copper refinery slag;*
- *Part 4: Coal furnace slag;*
- *Part 5: Nickel refinery slag;*
- *Part 6: Iron furnace slag;*
- *Part 7: Fused aluminium oxide;*
- *Part 8: Olivine sand;*
- *Part 9: Staurolite;*
- *Part 10: Almandite garnet.*

At the time of publication of this part of ISO 11126, part 10 was in the course of preparation. Part 2 has been deleted.

WARNING — Equipment, materials and abrasives used for surface preparation can be hazardous if used carelessly. Many national regulations exist for those materials and abrasives that are considered to be hazardous during or after use (waste management), such as free silica or carcinogenic or toxic substances. These regulations are therefore to be observed. It is important to ensure that adequate instructions are given and that all required precautions are exercised.

1 Scope

This part of ISO 11126 specifies requirements for staurolite abrasives, as supplied for blast-cleaning processes. It specifies ranges of particle sizes and values for apparent density, Mohs hardness, moisture content, conductivity of aqueous extract and water-soluble chlorides.

The requirements specified in this part of ISO 11126 apply to abrasives supplied in the “new” condition only. They do not apply to abrasives either during or after use.

Test methods for non-metallic blast-cleaning abrasives are given in the various parts of ISO 11127.

NOTE 1 Information on commonly referenced national standards for non-metallic abrasives is given in Annex A.

NOTE 2 Although this part of ISO 11126 has been developed specifically to meet requirements for preparation of steelwork, the properties specified will generally be appropriate for use when preparing other material surfaces, or components, using blast-cleaning techniques. These techniques are described in ISO 8504-2:1992. *Preparation of steel substrates before application of paints and related products — Surface preparation methods — Part 2: Abrasive blast-cleaning.*

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 11126. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 11126 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 11127-1:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 1: Sampling*

ISO 11127-2:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 2: Determination of particle size distribution*

ISO 11127-3:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 3: Determination of apparent density*

ISO 11127-4:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 4: Assessment of hardness by a glass slide test*

ISO 11127-5:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 5: Determination of moisture*

ISO 11127-6:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 6: Determination of water-soluble contaminants by conductivity measurement*

ISO 11127-7:1993, *Preparation of steel substrates before application of paints and related products — Test methods for non-metallic blast-cleaning abrasives — Part 7: Determination of water-soluble chlorides*

3 Term and definition

For the purposes of this part of ISO 11126, the following term and definition apply.

3.1 staurolite

a material manufactured from the naturally occurring mineral staurolite which is washed, dried, sieved, magnetically separated, and prepared for use as a blast-cleaning abrasive

NOTE Staurolite is an iron/aluminium silicate with the approximate chemical formula $\text{FeAl}_5\text{SiO}_{12}\text{OH}$.

4 Designation of abrasives

Staurolite sand abrasives shall be identified by "Abrasive ISO 11126" and the abbreviation N/ST indicating non-metallic staurolite abrasive. This shall be followed, without spaces, by an oblique stroke, and then the symbol S to indicate the required particle shape of the abrasive, when purchased, as shot.

The designation shall be completed by numbers denoting the particle size range, in millimetres, required (see Table 1).

NOTE Although staurolite is designated as a shot material, the grit comparator is used when assessing the profile produced. This is due to it having an irregular grain shape.

EXAMPLE

Abrasive ISO 11126 N/ST/S 0,2–0,6

denotes an abrasive of the non-metallic staurolite type, complying with the requirements of this part of ISO 11126, of initial particle shape shot and particle size range 0,2 to 0,6 mm.

It is essential that this full product designation is quoted on all orders.

5 Sampling

Sampling procedures shall be as specified in ISO 11127-1.

6 Requirements

6.1 General requirements

Staurolite abrasives shall be free from corrosive constituents and adhesion-impairing contaminants. Foreign, harmful impurities shall not be permitted.

Silica in staurolite abrasives shall be present as bonded silicate.

6.2 Particular requirements

Particular requirements for staurolite abrasives shall be as specified in Table 2.

7 Identification and marking

All materials shall be clearly marked or identified using the appropriate designation as specified in Clause 4, either directly or by the accompanying delivery note.

8 Information to be supplied by the manufacturer or supplier

The manufacturer or supplier shall supply, if requested, a test report detailing results for any relevant property as determined by the appropriate method specified in Table 2.

Table 1 — Particle size distribution

Particle size range ^a mm			0,1 to 0,3	0,1 to 0,4	0,2 to 0,6
Oversize	Sieve size	mm	0,3	0,4	0,6
	Residue, % (<i>m/m</i>)	max.	10	10	10
Nominal size	Sieve size	mm	0,1	0,1	0,2
	Residue, % (<i>m/m</i>)	min.	85	85	85
Undersize	Sieve size	mm	0,1	0,1	0,2
	Through-flow, % (<i>m/m</i>)	max.	5	5	5

^a By agreement between the interested parties, abrasives of different particle size ranges may be mixed together. Details of proportions of nominal size, oversize and undersize shall be specified. The maximum particle size shall not exceed 3,15 mm and the proportion of particles less than 0,1 mm shall not exceed 5 % (*m/m*).

Table 2 — Particular requirements for staurolite abrasives

Property		Requirement	Test method
Particle size range and distribution		See Table 1	ISO 11127-2
Apparent density	kg/m ³ [kg/dm ³]	(3,6 to 3,7) × 10 ³ [3,6 to 3,7]	ISO 11127-3
Mohs hardness ^a		min. 6	ISO 11127-4
Moisture	% (m/m)	max. 0,2	ISO 11127-5
Conductivity of aqueous extract	mS/m	max. 25	ISO 11127-6
Water-soluble chlorides	% (m/m)	max. 0,002 5	ISO 11127-7
^a Another method of assessing hardness may be used, together with an appropriate minimum requirement, by agreement between the interested parties.			

Bibliography

Commonly referenced national standards for non-metallic abrasives are as follows:

- [1] DIN 8200:1982, *Strahlverfahrenstechnik; Begriffe, Einordnung der Strahlverfahren* (Blasting; terms, classification of blasting techniques).
- [2] DIN 8201-5:1985, *Feste Strahlmittel, natürlich, mineralisch; Quarzsand* (Natural mineral abrasives; quartz sand).
- [3] DIN 8201-6:1985, *Feste Strahlmittel, synthetisch, mineralisch, Elektrokorund* (Synthetic mineral abrasives; electric corundum).

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.